

Application No. 10/766,939  
Reply to Office Action dated February 5, 2007

Attorney Docket No. FS-F03228-01

### **Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

### **Listing of the Claims:**


1. (Currently amended): An image forming method comprising:  
image-wise exposing to a radiation source a photothermographic material comprising, on a same surface of a support, a photosensitive silver halide having a silver iodide content of 40 to 100 mol%, a non-photosensitive organic silver salt of an aliphatic carboxylic acid including a silver behenate, a reducing agent, a binder, and an adsorbable redox compound represented by Formula (I), wherein, in Formula (I), A represents a group that can be adsorbed by silver halide; W represents a divalent connecting group; n represents 0 or 1; B represents a reducing group that is capable of reducing silver ions and is a residue derived from a compound represented by any one of Formulas B<sub>1</sub> to B<sub>5</sub> and Formula B<sub>13</sub>; and  
thermally developing the image-wise exposed photothermographic material with a developing time of 1 to 12 seconds;  
wherein in Formulas B<sub>1</sub> to B<sub>5</sub> and in Formula B<sub>13</sub>, R<sub>b1</sub>, R<sub>b2</sub>, R<sub>b3</sub>, R<sub>b4</sub>, R<sub>b5</sub>, R<sub>b13</sub>, R<sub>N1</sub>, R<sub>N2</sub>, R<sub>N3</sub>, R<sub>N4</sub> and R<sub>N5</sub> each independently represent a hydrogen atom, an alkyl group, an aryl group or a heterocyclic group; R<sub>H3</sub>, R<sub>H5</sub>, R'<sub>H5</sub>, and R<sub>H13</sub> each independently represent a hydrogen atom, an alkyl group, an aryl group, an acyl group, an alkylsulfonyl group or an arylsulfonyl group, in which R<sub>H3</sub> may alternatively represent a hydroxy group; R<sub>b130</sub> to R<sub>b133</sub> each independently represent a hydrogen atom or a substituent; and m<sub>5</sub> represents 0 or 1;

Formula (I)     A-(W)<sub>n</sub>-B


Application No. 10/766,939  
 Reply to Office Action dated February 5, 2007

Attorney Docket No. FS-F03228-01


(B<sub>1</sub>)




(B<sub>2</sub>)




(B<sub>3</sub>)




(B<sub>4</sub>)



(B<sub>5</sub>)



(B<sub>13</sub>)




wherein the photothermographic material further includes a compound represented by the following formula (H):



wherein in formula (H), Q represents an alkyl group, an aryl group or a heterocyclic group; Y represents a divalent connecting group; n represents 0 or 1; Z<sub>1</sub> and Z<sub>2</sub> each independently represent a halogen atom; and X represents a hydrogen atom or an electron attracting group

and wherein the reducing agent is a compound represented by the following formula (R-1):

Formula (R-1)



wherein in formula (R-1), R<sup>11</sup> and R<sup>11'</sup> each independently represent an alkyl group having 1 to 20 carbon atoms; R<sup>12</sup> and R<sup>12'</sup> each independently represent an alkyl group having 2 to 20 carbon atoms; L represents a -S- group or a -CHR<sup>13</sup>- group; R<sup>13</sup> represents a hydrogen atom or an alkyl group having 1 to 20 carbon atoms; X<sup>1</sup> and X<sup>1'</sup> each independently represent a hydrogen atom or a group that can substitute a benzene ring.

Application No. 10/766,939  
Reply to Office Action dated February 5, 2007

Attorney Docket No. FS-F03228-01

2. (Original): The image forming method according to claim 1, wherein the developing time is 2 to 10 seconds.
3. (Original): The image forming method according to claim 1, wherein the thermal development is conducted at a temperature of 80 to 250° C.
4. (Original): The image forming method according to claim 1, wherein the thermal development is conducted at a temperature of 100 to 140° C.
5. (Original): The image forming method according to claim 1, wherein the photothermographic material further includes an antifogging agent.
6. (Original): The image forming method according to claim 1, wherein the photosensitive silver halide has an average grain size of 5 to 50 nm.
7. (Original): The image forming method according to claim 1, wherein the photothermographic material further includes a development accelerator.
8. (Cancelled.)
9. (Original): The image forming method according to claim 1, wherein the photothermographic material further includes a toning agent.
10. (Original): The image forming method according to claim 1, wherein the photothermographic material further includes an ultra-high contrast agent.
11. (Original): The image forming method according to claim 1, wherein the photothermographic material further includes a matting agent.
12. (Previously Presented): The image forming method according to claim 1, wherein the radiation source is a laser.

Application No. 10/766,939  
Reply to Office Action dated February 5, 2007

Attorney Docket No. FS-F03228-01

13. (previously presented): The image forming method according to claim 12, wherein the laser has a light emission peak intensity within a wavelength range of 350 to 450 nm.

Claims 14-20 (Cancelled.)


21. (Previously presented): The method of claim 1 wherein the silver halide has a silver iodide content of 80 to 100 mol%.

22. (Previously presented): The method of claim 1 wherein the silver halide has a silver iodide content of 90 to 100 mol%.

23. (Previously presented): The method of claim 1, wherein an adsorbable group represented by A is a mercapto group, a salt thereof, a thion group ( $-C(=S)-$ ), a heterocyclic group containing at least an atom selected from a nitrogen atom, a sulfur atom, a selenium atom and a tellurium atom, a sulfide group, a disulfide group, a cationic group, or an ethynyl group.









24. (Previously presented): The method of claim 1, wherein the adsorbable redox compound is represented by any of the following formulas (1) to (38) and (71) to (81):

Attorney Docket No. FS-F03228-01















Application No. 10/766,939  
Reply to Office Action dated February 5, 2007

Attorney Docket No. FS-F03228-01











Application No. 10/766,939  
Reply to Office Action dated February 5, 2007.

Attorney Docket No. FS-F03228-01



Application No. 10/766,939  
Reply to Office Action dated February 5, 2007












Attorney Docket No. FS-F03228-01





Application No. 10/766,939  
Reply to Office Action dated February 5, 2007

Attorney Docket No. FS-F03228-01



Application No. 10/766,939  
Reply to Office Action dated February 5, 2007

Attorney Docket No. FS-F03228-01

25. (cancelled)

26. (Previously presented): The method of claim 1, wherein the photothermographic material further comprises a compound represented by the following formula (H):

Formula (H)             $Q-(Y)_n-C(Z_1)(Z_2)X$

wherein in formula (H), X is a bromine atom; Y is SO<sub>2</sub>; N is 1; and Q is an aryl group or a heterocyclic group.